

# SiSiB® PC2720 SILANE

- 1 -

## CHEMICAL NAME

3-isocyanatepropyltriethoxysilane

### CHEMICAL STRUCTURE

$$O \longrightarrow C \longrightarrow N \longrightarrow (CH_2)_3 \longrightarrow Si \longrightarrow OC_2H_5$$
  
 $OC_2H_5$   
 $OC_2H_5$ 

### INTRODUCTION

SiSiB® PC2720 is an isocyanate functional silane. It is used for the functionalization of numerous compounds with active hydrogen atoms. SiSiB® PC2720 hydrolyzes in the presence of moisture to form silanols, which can react with themselves to produce siloxanes.

### TYPICAL PHYSICAL PROPERTIES

CAS No.	24801-88-5
EINECS No.	246-467-6
Formula	C <sub>10</sub> H <sub>21</sub> NO <sub>4</sub> Si
Molecular Weight	247.36
Boiling Point	238°C [760mmHg]
Flash Point	80°C
Color and Appearance	Colorless transparent liquid
Density <sub>25/25°C</sub>	1.00
Refractive Index	1.421 [25°C]
Active Purity	98.0%

### APPLICATIONS

SiSiB® PC2710 and SiSiB® PC2720 can be used as crosslinkers for one part moisture



Copyright© 2009 Power Chemical Corporation Ltd. SiSiB® is a registered trademark of PCC. For more knowledge regarding organosilanes, you may visit www.SiSiB.com or www.PCC.asia



# SiSiB® PC2720 SILANE

- 2 -

curable urethane adhesives, sealants and coatings.

SiSiB® PC2710 and SiSiB® PC2720 can be used as adhesion promoters for one part moisture curable and two part reactive urethane systems.

SiSiB® PC2710 and SiSiB® PC2720 can be used as adhesion promoters for silicone sealants or coatings, to enhance adhesion to organic substrates with active hydrogen atoms.

SiSiB® PC2710 and SiSiB® PC2720 can provide good wet adhesion to glass, metal and other inorganic substrates, and can provide good thermal, chemical and UV stable performance.

SiSiB® PC2720 hydrolyzes slower than SiSiB® PC2710. SiSiB® PC2720 is better for applications requring greater open time or enhanced shelf stability.

#### PACKING AND STORAGE

SiSiB® PC2720 is supplied in 20Kg plastic drum, 190Kg steel drum or 950Kg IBC container.

In the unopened container SiSiB® PC2720 has a shelf life of one year.

#### Notes

All information in the leaflet is based on our present knowledge and experience. We reserve the right to make any changes according to technological progress or further developments. Performance of the product described herein should be verified by testing.

We specifically disclaim any other express or implied warranty of fitness for a particular purpose or merchantability. We disclaim liability for any incidental or consequential damages.

Please send all technical questions concerning quality and product safety to: silanes@SiSiB.com.



Copyright© 2009 Power Chemical Corporation Ltd. SiSiB® is a registered trademark of PCC. For more knowledge regarding organosilanes, you may visit www.SiSiB.com or www.PCC.asia